

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



⑪ Publication number : **0 586 109 A2**

⑫ **EUROPEAN PATENT APPLICATION**

⑲ Application number : **93306276.2**

⑤① Int. Cl.⁵ : **C08L 23/10, C08J 5/18**

⑳ Date of filing : **09.08.93**

③① Priority : **11.08.92 JP 214040/92**

④③ Date of publication of application :
09.03.94 Bulletin 94/10

⑥④ Designated Contracting States :
DE FR GB IT

⑦① Applicant : **SUMITOMO CHEMICAL
COMPANY, LIMITED**
5-33 Kitahama 4-chome Chuo-ku
Osaka-shi Osaka (JP)

⑦② Inventor : **Sadatoshi, Hajime**
1-9-546, Yushudainishi
Ichihara-shi, Chiba (JP)
Inventor : **Ima, Seichiro**
1-9-923, Yushudainishi
Ichihara-shi, Chiba (JP)
Inventor : **Tanimura, Hiroyuki**
504, 98, Daijuku
Sodegaura-shi, Chiba (JP)

⑦④ Representative : **Diamond, Bryan Clive et al**
Gee & Co. Chancery House Chancery Lane
London WC2A 1QU (GB)

⑤④ **Polypropylene compositions and films thereof.**

⑤⑦ A crystalline propylene polymer (100 parts by wt) which can be a random copolymer with an olefin, having a molecular weight distribution (Mw/Mn) of less than 5.0 and preferably a melt flow rate of 3.0 to 50 g/10 minutes, is compounded with 0.001 to 1.0 part of a crystal nucleating agent which can be inorganic, organic or polymeric (e.g. talc, an aromatic carboxylic acid metal salt or a vinyl cycloalkane polymer), preferably of mean particle size 6.0 µm or less, such that the crystallization temperature of the composition is at least 1.5°C, preferably 2.0°C, higher than that of the propylene polymer. Synthesis of the polymer is described with a Ziegler-Natta catalyst.

The composition is used for melt-extrusion of a film of thickness 10 to 500 µm by a T-die film-forming method in which the surface temperature of the cooling roll is at least 50°C. Multilayer films can be co-extruded.

The films have good transparency, which has low dependency on the film thickness, and are useful for packaging.

EP 0 586 109 A2

Jouve, 18, rue Saint-Denis, 75001 PARIS

The present invention relates to a polypropylene composition and films thereof. More specifically, the invention relates to a polypropylene composition having an excellent transparency and showing a small film-forming condition dependency of the transparency, and to a film made of the polypropylene composition.

Since a polypropylene film has excellent appearance, heat resistance, rigidity, etc., the film is widely used for the packaging of food, fibers and other products.

Recently, high-speed film formation by a large-sized film-forming machine has been practiced to improve the productivity of its formation, and also various thicknesses of films have been employed to widen the field of use. In this case, as a result thereof, the cooling condition at film formation changes, which has large effects on the transparency of the film formed, and a problem occurs that the transparency of the film, which is good at a low-speed film formation or in thin films having a thickness of from about 20 to 30 μm , is greatly reduced at high-speed film formation or in films having a thickness of at least 50 μm .

To overcome the problem, attempts have been made to decrease the surface temperature of a cooling roll by decreasing the temperature of the cooling water, or to directly cool a molten resin extruded with water without using a cooling roll, and some improved effect has been obtained. However, the influences caused by the temperature of cooling water and deviation of the flow rate cannot be avoided, and an adequate improvement has not yet been obtained.

Thus, development of a polypropylene composition and a polypropylene film having a good transparency showing a small film-forming condition dependency and a small thickness dependency of the transparency has been desired.

A reforming method of thermally decomposing or peroxide-decomposing a polypropylene resin, and a method of compounding a polypropylene resin with a sorbitol nucleating agent, are known, for improving the transparency of a polypropylene film.

In the reforming method of decomposing a polypropylene resin, the improvement effect may be obtained at low-speed film formation when the surface temperature of a cooling roll is low, but no effect is obtained at high-speed film formation when the surface temperature of a cooling roll is high. Further, in the case of high-speed film formation of thick films, the transparency is greatly reduced.

Also, in the method of compounding a sorbitol nucleating agent, the effect of improving the transparency may be obtained, but since use of the sorbitol nucleating agent causes an unpleasant odor of the film obtained, its use is restricted.

Accordingly, an object of the present invention is to provide a polypropylene composition and a film thereof having a good transparency and showing a small film-forming condition dependency and a small thickness dependency of the transparency without reducing the preferred characteristics which the polypropylene film inherently possesses.

As a result of various investigations to develop a polypropylene composition and a film thereof having a good transparency and showing a small film-forming condition dependency and a small thickness dependency of the transparency, it has been found that the problem of the prior art can be overcome by using a polymer having a molecular weight distribution in a specific range as a crystalline propylene polymer and compounding the polymer with a specific amount of a crystal nucleating agent, to obtain a polypropylene composition having a crystallization temperature higher than the crystallization temperature of the crystalline propylene polymer by at least a specific temperature.

Thus, according to one embodiment of the present invention, there is provided a polypropylene composition comprising 100 parts by weight of a crystalline propylene polymer having a molecular weight distribution (Mw/Mn) of less than 5.0 and from 0.0001 to 1.0 part by weight of a crystal nucleating agent, the composition having a crystallization temperature at least 1.5°C higher than the crystallization temperature of the crystalline propylene polymer.

According to another embodiment of the present invention, there is provided a polypropylene film formed by melt-extruding the above-described polypropylene composition.

The crystalline propylene polymer used in the present invention has a molecular weight distribution (Mw/Mn) of less than 5.0. If the molecular weight distribution of the crystalline propylene polymer is higher than 5.0, a polypropylene composition and the film thereof having excellent transparency and showing a small film-forming condition dependency of the transparency, which are the objects of the present invention, cannot be obtained. The molecular weight distribution is preferably 4.5 or less and more preferably 4.0 or less.

The crystalline propylene polymer used in the present invention is a crystalline propylene homopolymer or a crystalline propylene- α -olefin copolymer.

Examples of the crystalline- α -olefin copolymer are a propylene-ethylene copolymer, a propylene-butene-1 copolymer and a propylene-ethylene-butene copolymer, which are substantially random copolymers. A mixture thereof may be used if the molecular weight distribution thereof is less than 5.0.

A preferred crystalline propylene copolymer used in the present invention is a crystalline propylene- α -ole-

fin copolymer having a melting point of 150°C or less and an α -olefin content of from 2.0 to 30% by weight, from the point of the improving effect of the film-forming condition of the transparency.

A crystalline propylene polymer having a melt flow rate of from 3.0 to 50 g/10 minutes is also preferable, to provide transparency and high speed workability.

6 The crystalline propylene polymer having a molecular weight distribution of less than 5.0 can be preferably produced by polymerization using a Ziegler-Natta catalyst containing Ti, Mg and Cl as the essential components.

The crystalline propylene polymer can also be produced by a conventional method such as a method of decomposing the propylene polymer having a molecular weight distribution of at least 5.0 obtained by using the catalyst described in JP-A-47-34478 (the term "JP-A" as used herein means an unexamined published Japanese patent application), or a method of thermally decomposing the propylene polymer.

10 The crystal nucleating agent used in the present invention can be any crystal nucleating agent if the agent meets the requirement that by compounding 100 parts by weight of the crystalline polypropylene with from 0.0001 to 1.0 part by weight of the crystal nucleating agent, the crystallization temperature of the composition of the crystalline polypropylene compounded with the crystal nucleating agent is at least 1.5°C higher than the crystallization temperature of the crystalline propylene polymer.

Examples of the crystal nucleating agent are an inorganic crystal nucleating agent, an organic crystal nucleating agent, a polymeric crystal nucleating agent, and the α -crystal nucleating agents for propylene. An example of an inorganic crystal nucleating agent is talc, examples of an organic crystal nucleating agent are aromatic carboxylic acid metal salts (e.g., aluminum p-tert-butylbenzoate or sodium p-tert-butylbenzoate), aromatic carboxylic acids, and aromatic phosphoric acid metal salts; and examples of a polymeric crystal nucleating agent are polymers of 3-position branched olefins having at least 5 carbon atoms (e.g., 3,3-dimethylbutene-1, 3-methylbutene-1, 3-methylpentene-1, 3-methylhexene-1 or 3,5,5-trimethylhexene-1) and vinylcycloalkanes (e.g., vinylcyclopentane, vinylcyclohexane or vinylnorbornane). Of these crystal nucleating agents, talc, the aromatic carboxylic acid metal salts, and the vinylcycloalkane polymers are preferably used.

25 The crystal nucleating agent is compounded with the crystalline propylene polymer in an amount of from 0.0001 to 1.0 part by weight per 100 parts by weight of the crystalline propylene polymer. It is important that the crystal nucleating agent is compounded such that the crystallization temperature of the composition compounded with the crystal nucleating agent is at least 1.5°C higher ($\Delta T_c \geq 1.5^\circ\text{C}$) than the crystallization temperature of the crystalline propylene polymer. Even when ΔT_c is higher than at least 1.5°C, if the amount of the crystal nucleating agent compounded is outside the above-described range defined by the present invention, the effect of the present invention is not obtained as regards the transparency or the film-formation condition dependency and the thickness dependency of the transparency. Also, even when the amount of the crystal nucleating agent compounded is in the range defined in the present invention, if ΔT_c is lower than 1.5°C, the effect of the present invention is not obtained.

35 The amount of the crystal nucleating agent compounded is preferably from 0.0003 to 0.5 part by weight and also T_c is preferably at least 2.0°C.

The mean particle size of the crystal nucleating agent used in the present invention is preferably 6.0 μm or less, and more preferably 4.5 μm or less, to avoid deterioration of the appearance of the film due to occurrence of "fish eyes".

40 To produce the composition of the invention, suitable methods include previously melt-kneading the crystalline propylene polymer with the crystal nucleating agent, compounding the crystal nucleating agent with the crystalline propylene polymer and melt-kneading the mixture during the film formation, and compounding the master batch of the crystal nucleating agent with the crystalline propylene polymer, but any method wherein the composition within the range defined in the present invention is formed at the film formation can be used.

45 The polypropylene composition of the present invention can contain, if necessary, various additives conventionally used, such as an antioxidant, a neutralizing agent, a lubricant, an antiblocking agent or an antistatic agent.

50 The polypropylene composition of the present invention is suitably used for the production of a melt-extruded product having a thickness of from 10 to 500 μm in a T-die film-forming method under the condition that the surface temperature of the cooling roll is at least 50°C, and is particularly used for the production of an unstretched film having a thickness of from 10 to 100 μm .

Also, since the polypropylene composition of the present invention has the preferred characteristics described above, the composition is suitably used as a component for at least one layer in the production of a multilayer film by a co-extrusion film-forming method.

55 The method of producing the polypropylene film of the present invention is not particularly limited, and can be a method which is conventionally used industrially, i.e., a method of producing a polypropylene film by a melt-extruding molding method such as a T-die film-forming method, a tubular film-forming method, etc. Of

those, a T-die film-forming method wherein a high-speed film formation can be practiced by a large-size film-forming machine is preferably used.

The present invention is described in more detail by the following examples.

The method of measurement of each property referred to herein, including in the examples, was as follows.

(1) Melt Flow Rate (MFR):

The MFR of the crystalline propylene polymer was measured by the method of Condition-14 according to JIS K7210.

(2) Molecular Weight Distribution (Mw/Mn):

The molecular weight distribution was measured by G.P.C. (Gel Permeation Chromatography) under the following conditions:

Machine Type:	150CV Type (manufactured by Millipore Waters Co.)
Column:	Shodex M/S 80
Measurement Temperature:	145°C
Solvent:	Orthodichlorobenzene
Sample Concentration:	5 mg/8 ml

When Standard Reference Material 706 (polystyrene of Mw/Mn = 2.1) of NBS (National Bureau of Standards) was measured under the above conditions, the molecular weight distribution (Mw/Mn) of 2.1 was obtained.

(3) Melting Temperature (Tm) and Crystallization Temperature (Tc):

After previously melting 10 mg of a test piece at 220°C for 5 minutes in a nitrogen gas atmosphere using a differential scanning calorimeter (Type DSC-7, quenching corresponding type, trade name, made by Perkin-Elmer Co.), the temperature thereof was decreased to 40°C at a temperature-lowering rate of 5°C/minute. In this case, the peak temperature of the maximum peak of the crystallization exothermic curve obtained was defined as the crystallization temperature (Tc).

Thereafter, the temperature was increased at a rate of 5°C/minute and the peak temperature of the maximum peak of the melting endothermic curve obtained was defined as the melting point (Tm).

In addition, the melting point of indium (In) measured at a temperature-increasing rate of 5°C/minute using the measurement machine described above was 156.6°C.

(4) Ethylene Content and Butene-1 Content

Ethylene Content: The ethylene content was determined by the IR spectral method described in Kohbunshi Bunseki (Polymer Analysis) Handbook, page 256 [(i) Random Copolymer], published by Asakura Shoten, 1985.

Butene-1 Content: The butene-1 content was determined by the IR spectral method.

$$\text{Butene-1 content (weight \%)} = 1.208K'$$

wherein K' is an absorbance at 767 cm⁻¹.

(5) Transparency (haze):

Measured according to JIS K7105.

Reference Example 1

(a) Synthesis of Organomagnesium Compound:

After replacing the inside atmosphere of a one liter flask equipped with a stirrer, a reflux condenser, a dropping funnel, and a thermometer with argon, 32.0 g of a shaved-form magnesium for a Grignard reagent was placed in the flask. Then, 120 g of butyl chloride and 500 ml of dibutyl ether were charged in the dropping funnel and about 30 ml of the mixture was dropped onto magnesium in the flask to initiate the reaction. After the initiation of the reaction, dropping of the mixture was continued at 50°C for 4 hours and thereafter, the reaction was further continued at 60°C for one hour. Thereafter, the reaction mixture was cooled to room temperature and solid components were filtered off.

When butylmagnesium chloride in dibutyl ether was hydrolyzed with 1N sulfuric acid and the concentration was determined by back-titration with an aqueous solution of 1N sodium hydroxide using phenolphthalein as the indicator, the concentration was 2.1 mols/liter.

(b) Synthesis of Solid Product

After replacing the inside atmosphere of a 500 ml flask equipped with a stirrer and a dropping funnel with argon, 240 ml of hexane, 5.4 g (15.8 mmols) of tetrabutoxytitanium, and 61.4 g (295 mmols) of tetraethoxysilane were placed in the flask to form a homogeneous solution. Then, 150 ml of the organomagnesium compound synthesized in the above step (a) was gradually added dropwise to the mixture from the dropping funnel over a period of 4 hours while keeping the temperature of the inside of the flask at 5°C. Thereafter, the resulting mixture was further stirred at room temperature for one hour and solids

formed were separated from liquid at room temperature, repeatedly washed 3 times with 240 ml of hexane and dried at reduced pressure to obtain 45.0 g of a light-brown solid product.

The solid product obtained contained 1.7% by weight of a titanium atom, 33.8% by weight of an ethoxy group, and 2.9% by weight of a butoxy group.

Also, in the wide angle X-ray diffraction diagram of the solid product by the Cu-K α line, no clear diffraction peaks were observed, which showed that the product had a noncrystalline structure.

(c) Synthesis of Ester-Treated Solid:

After replacing the inside atmosphere of 100 ml flask with argon, 6.5 g of the solid product synthesized in the above step (b), 16.2 ml of toluene, and 4.3 ml (16 mmols) of diisobutyl phthalate were placed in the flask and the reaction was carried out at 95°C for one hour.

After the reaction, solids formed were separated from liquid and washed 3 times with 33 ml of toluene.

(d) Synthesis of Solid Catalyst (activation treatment):

After finishing washing in the above step (c), 16.2 ml of toluene, 0.36 ml (1.3 mmols) of diisobutyl phthalate, 2.2 ml (13 mmols) of dibutyl ether, and 38.0 ml (346 mmols) of titanium tetrachloride were added to the solids in the flask and the reaction was carried out at 95°C for 3 hours. After finishing the reaction, solids formed were separated from liquid at 95°C and washed twice with 33 ml of toluene at the same temperature. Then, the above washing treatment with the mixture of diisobutyl phthalate, dibutyl ether, and titanium tetrachloride was repeated once more under the same condition and the solid product was washed 3 times with 33 ml of hexane to obtain 5.0 g of a loess-color solid catalyst.

The solid catalyst contained 2.1% by weight of titanium atoms, 19.9% by weight of magnesium, and 12.7% by weight of a phthalic acid ester.

Reference Example 2

[Preparation of Solid Catalyst]

(a) Synthesis of Solid Product

After replacing the inside atmosphere of a 5 liter flask equipped with a stirrer and a dropping funnel with argon, 1,100 ml of n-heptane and 670 ml of tetra-n-butoxytitanium were placed in the flask and the temperature in the flask was kept at 35°C. Then, a solution of 1,080 ml of n-heptane and 445 ml of ethylaluminum sesquichloride was gradually added dropwise to the mixture from the dropping funnel over a period of 2 hours while keeping the temperature of the system at 35°C. Thereafter, the temperature was raised to 60°C and the mixture was stirred for one hour. Then, the reaction mixture was allowed to stand at room temperature, solids formed were separated from liquid, and after repeatedly washing with 1,000 ml of n-heptane 4 times, the solids were dried under a reduced pressure to obtain a red-brown solid product.

The solid product contained 5.2 mmols of titanium and 7.0 mm of a n-butoxy group in one gram thereof.

(b) Synthesis of Solid Catalyst Component:

After replacing the inside atmosphere of a one liter flask with argon, 54 g of the solid product obtained in the above step (a) and 270 ml of n-heptane were placed in the flask and the temperature in the flask was kept at 65°C. Then, 48 ml of di-n-butyl ether and 156 ml of titanium tetrachloride were added thereto and the reaction was carried out at 65°C for one hour. The reaction mixture obtained was allowed to stand at room temperature, solids formed were separated from liquid, and after repeatedly washing with 500 ml of n-heptane 4 times, the solids were dried under a reduced pressure to obtain a solid catalyst component (a).

Then, 600 ml of dehydrated and purified n-heptane, 16.5 mmols of diethylaluminum chloride, and 50 g of the solid catalyst component (a) obtained above were successively added into a one liter glass flask and after raising the temperature thereof to 60°C, while pressing the inside pressure of the flask to 200 mm Hg with propylene, the polymerization was carried out until the amount of propylene supplied became 40 g. Then, 170 ml of vinylcyclohexane was supplied to the reaction mixture over a period of one hour and the polymerization was further continued for 2 hours. The solid catalyst containing the polymers of propylene and vinylcyclohexane obtained was washed with dehydrated and purified n-heptane and dried to obtain 222 g of a solid catalyst (b) containing 40 g of a propylene polymer unit and 132 g of a vinylcyclohexane polymer unit.

[Production of Vinylcyclohexane Polymer Composition]:

Into a 0.33 m³ reaction vessel equipped with a stirrer made of SUS, the inside pressure of which was adjusted to 0.5 kg/cm² gauge at 35°C with propylene, were successively added 0.16 m³ of n-heptane, 1.2 mols of diethylaluminum chloride and 0.1 mol of methyl methacrylate. After adding thereto 150 g of the solid catalyst

(b) prepared above, 20 kg of propylene, and 75 liters of hydrogen, the temperature thereof was raised to 60°C, and the polymerization was initiated. Propylene was supplied such that the polymerization pressure was maintained at 6 kg/cm² gauge and the polymerization was continued by supplying hydrogen such that the concentration of the vapor phase was kept at 6% by volume and when the total supplied amount of propylene became 28 kg, the polymerization was finished.

The polymer slurry obtained was immediately introduced into a post treatment bath, and after stopping the polymerization with BuOH and washing the slurry with water at 60°C for 3 hours, solids formed were separated from liquid to obtain 8.5 g of a vinylcyclohexane polymer composition. The content of the vinylcyclohexane polymer in the composition was 0.05% by weight.

Example 1

(a) Catalyst Component

In a 250 liter reaction vessel equipped with a stirrer was placed 150 liters of sufficiently purified hexane and after sufficiently replacing the inside atmosphere in the system with a nitrogen gas, and 3.2 mols of triethylaluminum (hereinafter referred to as "TEA"), 0.32 mols of cyclohexylethyldimethoxy-silane (hereinafter referred to as "CHEDMS"), and the solid catalyst obtained in Reference Example 1 in an amount of 51.8 g calculated as Ti atom were added into the reaction vessel. While keeping the temperature of the system at 25°C, 2.8 kg of propylene was continuously added thereto over a period of 2 hours.

(b) Polymerization:

Using three polymerization baths each having an inside volume of from 20 to 45 m³, the catalyst component prepared in the above step (a) was supplied thereto such that the polymerization temperature became 75°C, the polymerization pressure became 20 kg/cm²G, and the average residence time became 6 hours and while simultaneously supplying thereto TEA and CHEDMS, a vapor-phase polymerization was carried out by continuously supplying propylene and hydrogen such that the H₂ concentration in the vapor-phase portion became 0.7%.

The polymer obtained had a melt flow rate (230°C) of 11.0 g/10 minutes, a molecular weight distribution (Mw/Mn) was 4.0, and the crystallization temperature (T_c) was 115.7°C.

After compounding 100 parts by weight of the crystalline propylene polymer thus obtained with 0.2 part by weight of talc (having a mean particle size of 2.2 µm, made by Nippon Talc K.K.), 0.05 part by weight of calcium stearate, 0.1 part by weight of Sumilizer BHT (trade name, made by Sumitomo Chemical Company, Limited) and 0.05 part by weight of Irganox 1010 (trade name, made by Ciba-Geigy AG) were added to the above mixture. After mixing the resulting mixture with a Henschel mixer, the mixture was melt-extruded to form pellets. The pellets obtained were melt-extruded by a T-die film-forming machine having a diameter of 50 mm at a die temperature of 250°C and cooled by a cooling roll to obtain an unstretched film.

In this case, the temperature of cooling water supplied to the cooling roll was changed to practice cooling at the levels of 30°C and 70°C. Thus, when the temperature of cooling water was 30°C, an unstretched film having a thickness of 30 µm was obtained and when the temperature of cooling water was 70°C, unstretched films having a thickness of 30 µm and 70 µm, respectively, were obtained. In this case, the surface temperatures of the cooling roll were 30°C and 66°C, respectively.

Comparative Example 1

By following the same procedure as in Example 1 using the crystalline propylene polymer except that talc was not compounded, a film was prepared and evaluated as in Example 1. The evaluation results are shown in Table 1 below.

Examples 2 and 3

By using a 23 liter polymerization bath equipped with a stirrer, propylene was continuously polymerized using the solid catalyst described in JP-A-47-34478, in the co-presence of diethylaluminum chloride, an electron donor, and hydrogen, using heptane as a solvent, at a polymerization temperature of 60°C, a polymerization pressure of 6 kg/cm² G, and a vapor-phase hydrogen concentration of 2.9%.

The polymer obtained had a melt flow rate of 12.0 g/10 minutes, a molecular weight distribution (Mw/Mn) of 6.1, and a crystallization temperature (T_c) of 116.2°C.

By using the crystalline propylene polymer thus obtained, the same procedures as in Example 1 and Comparative Example 1 were followed and films obtained were evaluated as in Example 1. The evaluation results are shown in Table 1 below.

Table 1

	Crystalline Propylene Composition				Crystal Nucleating Agent		Polypropylene Composition		
	Mw/Mn	α -Olefin content		Tm (°C)	Tc (°C)	Kind	Amount (Parts by weight)	Tc (°C)	ΔT_c (°C)
		Ethylene (wt%)	Butene-1 (wt%)						
Example 1	4.0	0	0	163.9	115.7	Talc	0.2	127.7	12.0
Comparative Example 1	4.0	0	0	163.9	115.7	-	-	115.7	0.0
Comparative Example 2	6.1	0	0	161.2	116.2	Talc	0.2	124.0	8.3
Comparative Example 3	6.1	0	0	161.2	116.2	-	-	116.2	0.0

Table 1 (cont'd)

	Transparency (Haze)(%)			
	Cooling Roll Water Temp.: 30°C		Cooling Roll Water Temp.: 70°C	
	Film thickness 30 μ m		Film thickness 70 μ m	
Example 1	3.7	5.3	5.9	
Comparative Example 1	0.7	11.1	27	
Comparative Example 2	4.4	7.4	9.2	
Comparative Example 3	2.5	11.3	21	

As is clear from the results shown in Table 1, it can be seen that in the unstretched films obtained by using the compositions of the present invention, the transparency of the films is stable at a good level in the cooling roll temperature range of from a low-temperature range to a high-temperature range and also in the range of the film thickness of from the range of a thin film to the range of a relatively thick film.

Example 2

By using the same catalyst system and polymerization method as in Example 1, a mixed system of propylene, ethylene, butene-1 was subjected a vapor-phase continuous polymerization at a polymerization temperature of 80°C, a polymerization pressure of from 7 to 15 kg/cm² G, and a H₂ concentration of 0.25%. Thus, a propylene-ethylene-butene-1 random copolymer having an ethylene content of 1.2% by weight and a butene-1 content of 10.2% by weight was obtained as a crystalline propylene copolymer. The copolymer obtained had a melt flow rate of 5.7 g/10 minutes, a molecular weight distribution of 3.0 and a crystallization temperature of 99.3°C.

After compounding 100 parts by weight of the copolymer with 0.05 part by weight of talc (mean particle

size 1.9 μm , made by Nippon Talc K.K.), 0.05 part by weight of calcium stearate, 0.15 part by weight of Irganox 1010 (trade name, made by Ciba-Geigy AG), 0.05 part by weight of Sandostab P-EPQ (trade name, made by Sandoz), 0.1 part by weight of erucic acid amide, and 0.15 part by weight of a fine silica powder (mean particle size 2.73 μm , Syloid 55, trade name, made by Fuji Davison Chemical Ltd.), a film was prepared in the same manner as in Example 1 and evaluated as in Example 1. The evaluation results are shown in Table 2 below.

Comparative Example 4

By following the same procedure as in Example 2 using the same crystalline propylene polymer as in Example 2 except that talc was not compounded, a film was prepared and evaluated as in Example 2. The evaluation results are shown in Table 2.

Examples 3 to 6

By following the same procedure as in Example 2 using the same crystalline propylene polymer as in Example 2 while changing the kind or the amount of the crystal nucleating agent used as shown in Table 2 below, each of the films was prepared and evaluated as in Example 2. The evaluation results of these films are shown in Table 2 below.

In addition, the crystal nucleating agents used in these examples are as follows.

- Example 3: Talc, mean particle size 2.2 μm , made by Nippon Talc K.K.
- Example 4: Talc, mean particle size 4.5 μm , made by Nippon Talc K.K.
- Example 5: PTBBA AJ #500, trade name, made by Dainippon Ink And Chemicals, Inc., mean particle size 4.5 μm
- Example 6: Vinylcyclohexane Polymer Composition obtained in Reference Example 2, mean particle size 1 μm or less

Comparative Examples 5 to 9

By following the same procedure as Example 2 using the same crystalline propylene polymer as in Example 2 while changing the kind or the amount of the crystal nucleating agent used as shown in Table 3 below, further films were prepared and evaluated as in Example 2. The evaluation results are shown in Table 3 below.

The crystal nucleating agents used in these comparative examples were as follows.

- Comparative Examples 5 and 6: Talc, mean particle size 2.2 μm , made by Nippon Talc K.K.
- Comparative Example 7: Vinylcyclohexane polymer composition obtained in Reference Example 2, mean particle size less than 1 μm
- Comparative Example 8: Softon SS-1800, made by Bihoku Funka Kogyo K.K., mean particle size 1.3 μm
- Comparative Example 9: Kisuma 5B, trade name, made by Kyowa Hakko Kagaku Co., Ltd., mean particle size 0.8 μm

Comparative Example 10

By the same polymerization method as in Comparative Example 2, a mixed system of propylene and butene-1 was continuously polymerized at a polymerization temperature of 50°C, a polymerization pressure of 5 kg/cm² G, and a vapor-phase hydrogen concentration of 4.5% to obtain a propyleneethylene-butene-1 random copolymer having an ethylene content of 2.1% by weight, a butene-1 content of 4.2% by weight, a melt flow rate of 3.9 g/10 minutes, and a molecular weight distribution of 5.2.

After compounding 100 parts by weight of the random copolymer with 0.2 part by weight of talc (mean particle size 2.2 μm), 0.05 part by weight of calcium stearate, 0.15 parts by weight of Irganox, 0.05 part by weight of Sandostab P-EPQ, 0.1 part by weight of erucic acid amide, and 0.15 part by weight of a fine silica powder, a film was prepared in the same manner as in Example 1 and evaluated as in Example 1. The evaluation results are shown in Table 3 below.

Comparative Example 11

By following the same procedure as in Comparative Example 10 using the random copolymer obtained in Comparative Example 10 except that talc was not added, a film was prepared and evaluated as in Comparative Example 10. The evaluation results are shown in Table 3.

Table 2

	Crystalline Propylene Composition				Crystal Nucleating Agent Kind	Amount (Parts by weight)	Polypropylene Composition		
	Mw/Mn	α-Olefin content		Tm (°C)			Tc (°C)	Tc (°C)	ΔTc (°C)
		Ethylene (wt%)	Butene-1 (wt%)						
Example 2	3.0	1.2	10.2	138.0	Talc	0.05	102.2	2.9	
Comparative Example 4	3.0	1.2	10.2	138.0	-	-	99.3	0.0	
Example 3	3.0	1.2	10.2	138.0	Talc	0.4	104.8	5.5	
Example 4	3.0	1.2	10.2	138.0	Talc	0.2	103.7	4.4	
Example 5	3.0	1.2	10.2	138.0	Aluminum p-tert- butylbenzo- ate	0.2	113.8	14.5	
Example 6	3.0	1.2	10.2	138.0	99.3	0.0005	112.0	12.7	

Table 2 (cont'd)

	Transparency (Haze)(%)			
	Cooling Roll		Cooling Roll	
	Water Temp.: 30°C		Water Temp.: 70°C	
	Film thickness		Film thickness	
	30 μ m		30 μ m	70 μ m
Example 2	1.4		3.3	3.8
Comparative Example 4	1.1		7.1	11.8
Example 3	3.0		3.9	4.4
Example 4	2.0		3.1	3.3
Example 5	3.3		4.2	5.0
Example 6	1.2		4.0	4.6

Table 3

	Crystalline Propylene Composition				Crystal Nucleating Agent		Polypropylene Composition	
	Mw/Mn	α -Olefin content		T _m (°C)	T _c (°C)	Amount (Parts by weight)	T _c (°C)	ΔT_c (°C)
		Ethylene (wt%)	Butene-1 (wt%)					
Comparative Example 5	3.0	1.2	10.2	138.0	99.3	0.001	100.2	0.9
Comparative Example 6	3.0	1.2	10.2	138.0	99.3	2.0	105.5	6.2
Comparative Example 7	3.0	1.2	10.2	138.0	99.3	0.00001	105.1	5.8
Comparative Example 8	3.0	1.2	10.2	138.0	99.3	0.2	99.8	0.5
Comparative Example 9	3.0	1.2	10.2	138.0	99.3	0.2	99.3	0.0
Comparative Example 10	5.2	2.1	4.2	139.1	99.0	0.2	107.4	8.4
Comparative Example 11	5.2	2.1	4.2	139.1	99.0	-	99.0	0.0

Table 3 (cont'd)

	Transparency (Haze)(%)			
	Cooling Roll Water Temp.: 30°C Film thickness 30 µm	Cooling Roll Water Temp.: 70°C Film thickness 30 µm	Cooling Roll Water Temp.: 70°C Film thickness 70 µm	
Comparative Example 5	1.1	6.5	7.9	
Comparative Example 6	15.2	16.8	17.4	
Comparative Example 7	1.2	7.5	10.9	
Comparative Example 8	3.1	9.0	13.4	
Comparative Example 9	1.4	7.5	10.5	
Comparative Example 10	6.8	9.1	10.4	
Comparative Example 11	5.7	7.8	15.2	

As described above, by using the polypropylene composition of the present invention, a film having a good transparency and a very small film-forming condition dependency and a very small thickness dependency of the transparency can be obtained without reducing the preferred characteristics the polypropylene film inherently possesses and the film can be suitably used for a high-speed film formation by melt extrusion.

Claims

1. A polypropylene composition comprising 100 parts by weight of a crystalline propylene polymer having a molecular weight distribution (Mw/Mn) of less than 5.0 and from 0.0001 to 1.0 part by weight of a crystal nucleating agent, the composition having a crystallization temperature at least 1.5°C higher than the crystallization temperature of the crystalline propylene polymer.
2. A polypropylene composition as claimed in Claim 1, wherein the crystalline propylene polymer has a melt

flow rate of from 3.0 to 50 g/10 minutes.

3. A polypropylene composition as claimed in Claim 1 or 2, wherein the crystalline propylene polymer is a crystalline propylene homopolymer or a crystalline propylene- α -olefin copolymer.
- 5 4. A polypropylene composition as claimed in Claim 3, wherein the crystalline propylene- α -olefin copolymer is a propylene-ethylene copolymer, a propylene-butene-1 copolymer or a propylene-ethylene-butene-1 copolymer.
- 10 5. A polypropylene composition as claimed in Claim 3, wherein the crystalline propylene- α -olefin copolymer has an α -olefin content of from 2.0 to 30% by weight.
6. A polypropylene composition as claimed in any preceding claim, wherein the crystalline propylene polymer has the molecular weight distribution of 4.5 or less.
- 15 7. A polypropylene composition as claimed in any preceding claim, wherein the crystalline propylene polymer has a molecular weight distribution of 4.0 or less.
8. A polypropylene composition as claimed in any preceding claim, wherein the crystal nucleating agent is an inorganic crystal nucleating agent, an organic crystal nucleating agent, a polymeric crystal nucleating agent, or α -crystal crystal nucleating agent for propylene.
- 20 9. A polypropylene composition as claimed in Claim 8, wherein the crystal nucleating agent is talc, an aromatic carboxylic acid metal salt or a vinyl cycloalkane polymer.
- 25 10. A polypropylene composition as claimed in any preceding claim, wherein the amount of the crystal nucleating agent is from 0.003 to 0.5 part by weight.
11. A polypropylene composition as claimed in any preceding claim, wherein the crystal nucleating agent has a mean particle size of 6.0 μm or less.
- 30 12. A polypropylene composition as claimed in Claim 11, wherein the crystal nucleating agent has a mean particle size of 4.5 μm or less.
13. A polypropylene composition as claimed in any preceding claim, having a crystallization temperature at least 2.0°C higher than the crystallization temperature of the crystalline propylene polymer.
- 35 14. A polypropylene film obtained by melt-extruding a polypropylene composition as claimed in any preceding claim.

40

45

50

55